

## **Technical Information Sheet**

## ALESTA AR400\*

Number: CFA602B1

Name:

April 15, 2020 AR400 Anodize Silver Type: Proprietary

Alesta Group Code: AC10100000016

**POWDER PROPERTIES** 

ASTM D5965-96, C Specific Gravity  $1.36 \pm 0.05$ 

> Theoretical Coverage 141 ft 2/lb/mil

ASTM D3451-92, 13 Mass Loss During Cure < 1%

> Recommended Shelf Life: 12 Months @ 75°F

**COATING PROPERTIES** 

**ASTM D523-89** Gloss at 60° 13-19

**DPC TM 10.219** PCI Powder Smoothness 8 **ASTM D2454-95** Overbake Resistance, Time 100% ASTM D3363-92a Pencil Hardness 2H **ASTM D2794-93** Direct Impact, Gardner 30 in/lbs

**ASTM D3359-97** Adhesion, Cross Hatch 5B Pass ASTM D522-93a Flexibility, Mandrel

**ASTM B117-97** Salt Spray 3000 hrs

AAMA 2604-05 High Performance Organic

Coatings on Aluminum

Extrusions

**CURE SCHEDULE:** 

(Time at substrate temperature)

10 Minutes @ 400°F

FILM THICKNESS: 2.0-3.0 Mils

Recommended for use in architectural applications such as window frames, cladding, shopfronts and other products where enhanced levels of exterior weatherability are required. This product meets requirements for AAMA 2604 as per the American Architectural Manufacturers Association and is based on proven polyester technology used globally in architectural. The metallic component of this premium exterior product is incorporated into the powder, vastly improving application and reclaim behavior when compared to traditional metallic coating powders.

Prepared 6/10/2020

**ROHS** 

**APPLICATION** 

Electrostatic Spray, Cold

Pretreatment: Chrome Phosphate

Substrate: Aluminum

9800 Genard Rd. Houston, TX 77041-7624 1-800-247-3886 Hilliard, OH 43026-1213 4130 Lyman Dr.

fax: 713-939-4027 1-800-667-9610 fax: 614-771-4139

1/8 in. dia., no fracture

Passed

ISO 9001:2015

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller inelature. Since inflaters of solitate preparation, application procedures, curing procedures and other incommence and content actors and affect occurring profit of the soliton, senior assumes no liability for coating failure other than to supply replacement material from a coating material prove to be defective. Customer will determine suitabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.





## **Technical Information Sheet**

## ALESTA AR400\*

Number: CFA602B1

Name: AR400 Anodize Silver Type: Proprietary

Alesta Group Code: AC10100000016

Axalta does not intentionally add any RoHS restricted substances to this product, and the product is in conformity with the essential requirements of the following directives of the European Parliament and of the Council: Directive 2015/863; Directive 2011/65/EU; Directive 2002/65/EU; and, Directive 2003/11/EU.

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-247-3886 fax: 713-939-4027 1-800-667-9610 fax: 614-771-4139



ISO 9001:2015

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material or a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

