

Technical Information Sheet

Number: GFB608W3

Royal Black Wrinkle Type: Glycouril Polyester

Alesta Group Code: IO04004000416

POWDER PROPERTIES

Name:

ASTM D5965-96, C Specific Gravity 1.35 ± 0.05

Theoretical Coverage 142 ft 2/lb/mil

ASTM D3451-92, 13 *Mass Loss During Cure* < 2.5%

Recommended Shelf Life: 12 Months @ 75°F

COATING PROPERTIES

 ASTM D523-89
 Gloss at 60°
 Visual

 DPC TM 10.219
 PCI Powder Smoothness
 N/A

ASTM D3363-92a

PCT FOWDER STROOTHINESS

N/A

ASTM D2454-95

Overbake Resistance, Time
100%

ASTM D3363-92a

Pencil Hardness

HB

ASTM D2794-93 Dir / Rev Impact, Gardner 120 / 40 in/lbs
ASTM D3359-97 Adhesion. Cross Hatch 5B Pass

ASTM D522-93a Flexibility, Mandrel 1/8 in. dia., no fracture

ASTM B117-97 Salt Spray 1,000 hrs

APPLICATION

Electrostatic Spray, Cold Substrate: 0.032 in. CRS

Pretreatment: Bonderite® 1000, Parcolene® 60

CURE SCHEDULE:

(Time at substrate temperature) 15 Minutes @ 375°F

FILM THICKNESS: 2.0-3.0 Mils

This product is designed to penetrate Faraday cage areas with good coverage using standard corona

discharge guns.

Prepared 6/11/2020

ROHS

Axalta does not intentionally add any RoHS restricted substances to this product, and the product is in conformity with the essential requirements of the following directives of the European Parliament and of the Council: Directive 2015/863; Directive 2011/65/EU; Directive 2002/65/EU; and, Directive 2003/11/EU.

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-247-3886 fax: 713-939-4027 1-800-667-9610 fax: 614-771-4139



ISO 9001:2015

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material or coating material proven to be defective. Customer will determine suitabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

