

Technical Information Sheet

ALESTA AR300*

Number: HFJ611M5

August 19, 2020

Name: BAP Bronze Alesta Group Code: AE50208000016

Type: HAA Polyester

POWDER PROPERTIES

ASTM D5965-96, C Specific Gravity

 1.54 ± 0.05

Theoretical Coverage

125 ft 2/lb/mil

ASTM D3451-92, 13

Mass Loss During Cure Recommended Shelf Life: < 1%

12 Months @ 75°F

COATING PROPERTIES

ASTM D523-89 Gloss at 60° 46-56 7

100%

DPC TM 10.219 ASTM D2454-95 PCI Powder Smoothness Overbake Resistance, Time

ASTM D3363-92a

Pencil Hardness 2H

ASTM D2794-93

Dir / Rev Impact, Gardner 140 / 140 in/lbs

ASTM D3359-97

Adhesion, Cross Hatch 5B Pass

ASTM D522-93a **ASTM B117-97**

Flexibility, Mandrel

1/8 in. dia., no fracture

UL DTOV2 Organic Coating

Salt Spray Steel Enclosures, Elect. Eq. 1,500 hrs Recognized

AAMA 2603-05

Organic Coatings on Aluminum

Extrusions

APPLICATION

Electrostatic Spray, Cold Substrate: 0.032 in. CRS

Pretreatment: Bonderite® 1000, Parcolene® 60

CURE SCHEDULE:

(Time at substrate temperature)

FILM THICKNESS: 2.0-3.0 Mils

10 Minutes @ 400°F

This coating has been developed to meet or exceed the requirements of AAMA 2603 on architectural

aluminum components.

Prepared 8/19/2020

ROHS

Axalta does not intentionally add any RoHS restricted substances to this product, and the product is in conformity with the essential requirements of the following directives of the European Parliament and of the Council: Directive 2015/863; Directive 2011/65/EU; Directive 2002/65/EU; and, Directive 2003/11/EU.

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213

1-800-247-3886 fax: 713-939-4027 fax: 614-771-4139 1-800-667-9610



ISO 9001:2015

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller inelature. Since inflaters of solitate preparation, application procedures, coming procedures and other incorrections and affect coating period series scotting, series assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.



^{*}This product meets the requirements of AAMA 2603.