

Technical Information Sheet

ALESTA AR400*

Number: HFJ660T0

March 25, 2020

Name: AR400 Brown Slate

Type: HAA Polyester

Alesta Group Code: SD43008000316

POWDER PROPERTIES

ASTM D5965-96, C Specific Gravity 1.49 ± 0.05

Theoretical Coverage 129 ft 2/lb/mil

Recommended Shelf Life: 24 Months @ 75°F

Visual

30 in/lbs

Passed

COATING PROPERTIES

ASTM D523-89 Gloss at 60°

DPC TM 10.219 PCI Powder Smoothness N/A
ASTM D2454-95 Overbake Resistance, Time 100%
ASTM D3363-92a Pencil Hardness 2H

ASTM D3363-92a Pencil Hardness
ASTM D2794-93 Direct Impact, Gardner

ASTM D3359-97 Adhesion, Cross Hatch 5B Pass

ASTM D522-93a Flexibility, Mandrel 1/8 in. dia., no fracture

ASTM B117-97 Salt Spray 3000 hrs

AAMA 2604-05 High Performance Organic

Coatings on Aluminum

Extrusions

CURE SCHEDULE:

(Time at substrate temperature)

10 Minutes @ 400°F or 15 Minutes @ 375°F

FILM THICKNESS: 2.5-3.5 Mils

Substrate: Aluminum

Electrostatic Spray, Cold

APPLICATION

Pretreatment: Chrome Phosphate

Recommended for use in architectural applications such as window frames, cladding, shopfronts and other products where enhanced levels of exterior weatherability are required. This product meets requirements for AAMA 2604 as per the American Architectural as per the American Architectural Manufactures Association and is based on proven polyester technology used globally in architectural market.

Prepared 6/17/2020

ROHS

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-247-3886 fax: 713-939-4027 1-800-667-9610 fax: 614-771-4139 TOUGH

ISO 9001:2015

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.





Technical Information Sheet

ALESTA AR400*

Number: HFJ660T0

Name: AR400 Brown Slate Type: <u>March 25, 2020</u>

Alesta Group Code: SD43008000316

Axalta does not intentionally add any RoHS restricted substances to this product, and the product is in conformity with the essential requirements of the following directives of the European Parliament and of the Council: Directive 2015/863; Directive 2011/65/EU; Directive 2002/65/EU; and, Directive 2003/11/EU.

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-247-3886 fax: 713-939-4027 1-800-667-9610 fax: 614-771-4139



ISO 9001:2015

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material or a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

