

Technical Information Sheet

Fas-Trac Service

NUMBER: PFHF40S6

2005 Gray TGIC April 7, 2020

Type: TGIC-Polyester

POWDER PROPERTIES

NAME:

ASTM D5965-96, C Specific Gravity 1.59 ± 0.05

Theoretical Coverage 121 ft²/lb/mil

Recommended Shelf Life: 12 Months @, 75°F

COATING PROPERTIES

DPC TM 10.219 PCI Powder Smoothness 6

ASTM D3363-92a Pencil Hardness 2H

ASTM D2794-93 Dir / Rev Impact, Gardner 60 / 40 in/lbs

ASTM D522-93a Flexibility, Mandrel 1/4 in. dia., no fracture

ASTM B117-97 Salt Spray 1,000 hrs

UL DTOV2 Organic Coating Steel Enclosures, Elect. Eq. Recognized

APPLICATION

Electrostatic Spray, Cold Substrate: 0.032 in. CRS

Pretreatment: Bonderite 1000®, Parcolene® 60

This is an Axalta Powder Coating Systems USA Fas-Trac product. This coating is designed with extended exterior durability properties. When compared under similar outdoor conditions to standard grade powder coatings of similar color, gloss and specific gravity, it will retain original appearance properties for a longer period.

Cure Schedule:

(Time at substrate temperature)
10 Minutes @ 400°F

Film Thickness: 2.0-3.0 Mils

Prepared 7/19/2021

ROHS

Axalta does not intentionally add any RoHS restricted substances to this product, and the product is in conformity with the essential requirements of the following directives of the European Parliament and of the Council: Directive 2015/863; Directive 2011/65/EU; Directive 2002/65/EU; and, Directive 2003/11/EU.

9800 Genard Rd. Houston, TX 77041-7624 1-800-247-3886 fax: 713-939-4027 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-667-9610 fax: 614-771-4139



WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material for a coating material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

