

Technical Information Sheet

Number: UFD608B1

Name: Matte 27 Gold

Alesta Group Code: PU10100000316

April 14, 2021

Type: Aliphatic Urethane Polyester

POWDER PROPERTIES

ASTM D5965-96, C Specific Gravity 1.51 ± 0.05

Theoretical Coverage 127 ft 2/lb/mil

ASTM D3451-92, 13 *Mass Loss During Cure* < 1%

Recommended Shelf Life: 12 Months @ 75°F

COATING PROPERTIES

 ASTM D523-89
 Gloss at 60°
 10-20

 DPC TM 10.219
 PCI Powder Smoothness
 6

 ASTM D2454-95
 Overbake Resistance, Time
 100%

 ASTM D3363-92a
 Pencil Hardness
 2H

ASTM D2794-93 Dir / Rev Impact, Gardner 30 / 0 in/lbs
ASTM D3359-97 Adhesion, Cross Hatch 5B Pass

ASTM D522-93a Flexibility, Mandrel 1/8 in. dia., no fracture

ASTM B117-97 Salt Spray 1,000 hrs
UL DTOV2 Organic Coating Steel Enclosures, Elect. Eq. Recognized

APPLICATION

Electrostatic Spray, Cold Substrate: Aluminum

Pretreatment: Chrome Phosphate

CURE SCHEDULE:

(Time at substrate temperature)
10 Minutes @ 400°F

FILM THICKNESS: 2.0-3.0 Mils

The metallic component of this product is incorporated into the powder, vastly improving application and reclaim behavior when compared to traditional metallic coating powders.

Prepared 4/19/2021

ROHS

Axalta does not intentionally add any RoHS restricted substances to this product, and the product is in conformity with the essential requirements of the following directives of the European Parliament and of the Council: Directive 2015/863; Directive 2011/65/EU; Directive 2002/65/EU; and, Directive 2003/11/EU.

9800 Genard Rd. Houston, TX 77041-7624 4130 Lyman Dr. Hilliard, OH 43026-1213 1-800-247-3886 fax: 713-939-4027 1-800-667-9610 fax: 614-771-4139



ISO 9001:2015

WARRANTY POLICY: Seller certifies that all coatings delivered to Customer in unopened factory filled containers meet all pertinent quality standards presented in its current published literature. Since matters of surface preparation, application procedures, curing procedures and other local factors that affect coating performance are beyond Seller's control, Seller assumes no liability for coating failure other than to supply replacement material proven to be defective. Customer will determine suitability of this product for its use and thereby assume all risks and liabilities in connection therewith. Seller will not be liable for any injuries, damages or other losses derived, directly or indirectly, from or as a consequence of Customer's use of the product. SELLER DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, RELATING TO ITS PRODUCTS AND THEIR APPLICATION, INCLUDING BUT NOT LIMITED TO WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSES.

